

LS2-6941

Optically clear silicone elastomer

DESCRIPTION

- Two-part, optically clear, solvent free, low viscosity silicone
- Cures at room temperature or rapidly with heat
- Offers good physical and electrical stability across a broad range of temperatures
- 1:1 Mix Ratio (Part A:B)

APPLICATION

- To provide protection of electronic components and assemblies against shock, vibration, moisture, ozone, dust, chemicals and other environmental hazards by potting or encapsulating
- For photonics applications such as HBLEDs, photo detectors, lasers, discrete optics and flat panel displays that require a 1.41 refractive index

PROPERTIES

Typical Properties	Average Result	Standard	NT-TM
Uncured:			
Appearance*	Transparent	ASTM D2090	002
Viscosity, Part A*	1,200 cP (1,200 mPas)	ASTM D1084, D2196	001
Viscosity, Part B*	800 cP (800 mPas)	ASTM D1084, D2196	001
Refractive Index*	1.41	ASTM D1747, D1218	018
Work Time*	5.5 hours	-	008
Volume Resistivity	1 x 10 ¹⁴ ohm-cm	ASTM D257, D4496	040
Cured: 30 minutes at 150°C (302°F)			
Durometer, Type A*	30	ASTM D2240	006
Tensile Strength*	120 psi (0.83 MPa)	ASTM D412	007
Elongation*	100 %	ASTM D412	007
Dielectric Strength	600 volts/mil (23.6 kV/mm)	ASTM D149	-
Moisture Absorption % gain after 168 hour exposure at 85°C (185°F) / 85% R.H.	0.10%	-	202
Ionic Content, Cl	<5 ppm	-	-
Ionic Content, K	<5 ppm	-	-

Typical Properties	Average Result	Standard	NT-TM
Ionic Content, Na	<10 ppm	-	-
Glass Transition (T _g)	-112°C	ASTM E831	-
Coefficient of Linear Thermal Expansion (0°C to 150°C)	337 ppm/°C (337 μm/m/°C)	ASTM E831	-

*Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications.

INSTRUCTIONS FOR USE

Mixing

Mix in a 1:1 ratio Part A to Part B, taking care to minimize air entrapment during mixing.

Vacuum Deaeration

Removed air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches Hg, to a container rated for use and of volume at least four times that of material being deaerated. Hold vacuum until presence of air is no longer evident.

Substrate Considerations

Cures in contact with most materials common to electronic assemblies. Exceptions include butyl and chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents. Units being encapsulated or potted should be clean and free of surface contaminants. Containers and dispensers being used should also be clean and dry. Cure inhibition can usually be prevented by washing all containers with cleaning solvent or volatilizing the contaminants by heating.

Note: Some bonding applications may require the use of a primer. NuSil Technology LS1-3200 silicone primer is recommended.

Adjustable Cure Schedule

Product cures at a wide range of cure times and temperatures to accommodate different production needs. [Contact](#) NuSil Technology for details.

OPERATING TEMPERATURE

The operating temperature range of a silicone in any application is dependent on many variables, including but not limited to: temperature, time of exposure, type of atmosphere, exposure of the material's surface to the atmosphere, and

Packaging

50 ml SxS Kit
 2 Pint Kit (910 g)
 2 Gallon Kit (7.28 kg)
 10 Gallon Kit (36.4 kg)

Warranty

12 Months

mechanical stress. In addition, a material's physical properties will vary at both the high and low end of the operating temperature range. This type of silicone typically remains flexible at extremely low temperatures and has been known to perform at -50°C (-58°F) as well as resist breakdown at elevated temperatures up to 200°C (392°F). The user is responsible to verify optical and mechanical performance of a material in a specific application.

ROHS AND REACH COMPLIANCE

Please [contact](#) NuSil Technology's Regulatory Compliance department with any questions or for further assistance

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written

warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#)

NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.